



# ETAPRIME ACRYL FILLER 4:1 HS

ET4400AF-10/G1L, grey  
ET4400AF-40/G 4L, grey

## Proizvod

Svestrani 2K akrilni temeljni premaz/punilo. Ovisno o razrjeđivanju, može se upotrijebiti kao a) temeljni premaz b) debeloslojno punilo c) temeljni premaz koji se nanosi "mokro na mokro"

## Podloge

Željezo, čelik, stakloplastika, stara boja i punila za konstrukcije



## Priprema podloge

U slučaju nanošenja na punilo/kit, suho obrusite površinu sa P180-P240. Temeljito očistite i odmastite. Koristite krpu za tešku prašinu.

## Uvjeti za nanošenje

18-22° C



## Omjer miješanja

Po volumenu 4:1 s učvršćivačem Etalon ET4401 brzim ili ekstra brzim



## Razrjeđivanje

a) temelj do 10% b) debeloslojni filer 0%  
c) temelj "mokro na mokro" 30%

## Otvoreno vrijeme

60-90 min pri 20°



## Viskoznost za nanošenje

a) 18-22 sec b) 25-30 sec c) 14-16 sec Ford cup 4



## Oprema za špricanje

Gravitacijski pištolj za špricanje  
a) 1.6-1.8mm b) 1.6-1.8mm c) 1.4mm



## Broj slojeva

a) 2 sloja b) 2-4 sloja c) 1-1.5 sloja



## Flash off

a) 8-10 min b) 10 min c) 0 min

## Debljina sloja

a) 50-80µm b) do 300µm c) 30-50µm



## Sušenje

pri 20° C a) 3-4 sata b) 4-5 sata c) premazivanje  
pri 60° C a) 30-40 min b) 30-40 min c) u 10 min



## Brušenje

Suho brušenje s P400 za pune boje i P500 za metalik

## HOS

IIB (c) 540g/l; 432 g/l

## Skladištenje

12 mjeseci

### Uvoznik za Hrvatsku:

Sig Sistemi d.o.o., Zagrebačka 13A, 10431 Sv.Nedelja, tel: 01 3370063, www.sigsistemi.hr, E-mail: info@sigsistemi.hr